




## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>6</sup> :</b> <b>G01N 33/34, 3/08, B65H 77/00</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 99/44058</b> <b>(43) International Publication Date:</b> 2 September 1999 (02.09.99)
<b>(21) International Application Number:</b> PCT/FI99/00138 <b>(22) International Filing Date:</b> 22 February 1999 (22.02.99) <b>(30) Priority Data:</b> 980428 25 February 1998 (25.02.98) FI <b>(71) Applicant (for all designated States except US):</b> VALMET CORPORATION [FI/FI]; Panuntie 6, FIN-00620 Helsinki (FI). <b>(72) Inventors; and</b> <b>(75) Inventors/Applicants (for US only):</b> MUSTONEN, Harri [FI/FI]; Kiulu 12 E 10, FIN-40520 Jyväskylä (FI). PAKARINEN, Pekka [FI/FI]; Kaakonkoipi 3 A 2, FIN-40340 Jyväskylä (FI). TAMMENOJA, Mika [FI/FI]; Laajavuorentie 9 C 28, FIN-40740 Jyväskylä (FI). <b>(74) Agent:</b> FORSSÉN & SALOMAA OY; Yrjönkatu 30, FIN-00100 Helsinki (FI).		<b>(81) Designated States:</b> AL, AM, AT, AT (Utility model), AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, CZ (Utility model), DE, DE (Utility model), DK, DK (Utility model), EE, EE (Utility model), ES, FI, FI (Utility model), GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SK (Utility model), SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i> <i>In English translation (filed in Finnish).</i>

**(54) Title:** METHOD FOR DETERMINATION OF AN IRREVERSIBLE STRETCH AND OF A DYNAMIC MODULUS OF ELASTICITY

**(57) Abstract**

The invention concerns a method for determination of an irreversible stretch and of a dynamic modulus of elasticity from a paper web (W). In the method, the irreversible stretch and the dynamic modulus of elasticity are determined from the paper web (W) by means of on-line measurement. The invention also concerns a method in which the quantities that have been determined are employed in the control of the papermaking process.



**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

Method for determination of an irreversible stretch  
and of a dynamic modulus of elasticity

5

The invention concerns a method for determination of an irreversible stretch and of a dynamic modulus of elasticity from a paper web. The invention also concerns a method for the control of a papermaking process.

10

It is known from the prior art that, in manufacture of paper and board material, it is necessary to monitor the properties of the web material during the process of manufacture. For the quality control, a number of prior-art on-line or off-line methods are available. As a result of a determination of the properties of the web material, it is possible to regulate different parameters that are used in papermaking. The aim of the regulation is a final product of optimal quality and good runnability of the machines.

Earlier, the significance of the cross-direction tension profile of a paper web both for the quality of the ultimate product and for the runnability of the machines has been realized. In the *applicant's FI Patent No. 94,066*, there is a thorough discussion of the significance of the tension profile for the smooth running of the process of manufacture and for the quality of the ultimate product.

25 In the *applicant's FI Patent No. 80,522*, a method and an equipment for measurement of the tension of a web are described. In said solution, the tension of the web is measured by, in the vicinity of the moving web, fitting a measurement rib, which has a face that is curved in the running direction of the web and in which rib there are pressure metering detectors placed in holes. An air cushion is formed between the moving web and the curved face, in which cushion the air pressure is directly proportional to the tension of the web. The tension of the web is measured indirectly by metering the pressure in the air cushion.

30

In the *FI Patent No. 62,419*, a method for measurement of a tension profile is described, which method is based on the speed of propagation of a plane wave. In this method, an acoustic impulse is produced in the web, and the travel time of the impulse is measured by means of a microphone.

5

In the *US Patents 2,755,032 and 3,057,574*, mechanical and pneumatic equipments of measurement and regulation have been suggested for measurement of the tension profile of a web. In these apparatuses, the web is pressed by means of two shoes, which produce a change in the running direction of the web, and, at the same time,  
10 a force directly proportional to the tension of the web is applied to the shoes.

Even though a number of on-line methods are available for examination of the tension profile and of other properties of a web material, it has been difficult to determine the irreversible stretch and the dynamic modulus of elasticity during the  
15 process. As a rule, these quantities are determined under laboratory conditions. For this purpose, separate samples must be taken from the web material, and the result of determination of the quantities is obtained only after a delay. Thus, it takes a great deal of time before the necessary adjustments in the process can be made on the basis of the results obtained from the laboratory.

20

The problems stated above and involved in the prior art have constituted a reason for the present invention.

The object of the present invention is to provide a novel method for determination  
25 of an irreversible stretch and of a dynamic modulus of elasticity from a paper web. The aim of the method in accordance with the method is to provide a possibility for rapid adjustment of the regulation parameters employed in the manufacture of paper after determination of the quantities concerned.

30 In view of achieving the objectives stated above and those that will come out later, the method in accordance with the invention for determination of an irreversible

stretch and of a dynamic modulus of elasticity from a paper web is mainly characterized in that the method comprises the following steps:

- the paper web is subjected to an on-line measurement of its cross-direction tension profile at two or more different tension levels,
- a curve is fitted to the number of points of tension measurement carried out at each location of measurement in the cross direction of the paper web,
- the irreversible stretch is determined from each fitted curve, and
- the dynamic modulus of elasticity is determined from each fitted curve.

10

The method in accordance with the invention for the control of a papermaking process is mainly characterized in that, in said method, the method in accordance with the invention for determination of an irreversible stretch and of a dynamic modulus of elasticity from a paper web is employed for regulation of the dynamic modulus of elasticity and/or of the irreversible stretch.

15

In carrying the method in accordance with the invention into effect, it is possible to use apparatuses of measurement of the cross-direction tension profile of a web which are known from the prior art and which have possibly already been installed in the paper machine. The tension profile is determined across the entire width of the paper web at two or more different tension levels, and the stretch between targets is determined as a measurement of difference in speed.

20

At each of the different points of measurement of the tension profile, the measurement results of a number of measured tension profiles are fitted together. From the fitted result thus formed, it is possible to determine the irreversible stretch and the modulus of elasticity of the paper web.

25

A particular advantage of the present invention is the rapidity of the method of measurement as well as the possibility of integrating the measurement procedure on-line in the rest of the control system of the paper machine.

30

In the following, the invention will be described in detail with reference to the exemplifying embodiments of the invention illustrated in the figures in the accompanying drawing, the invention being, however, not supposed to be confined to said embodiments alone.

5

Figure 1 illustrates a location of an apparatus for measurement of tension profile in a paper machine.

Figure 2 illustrates a result of measurement of a tension profile at three different  
10 levels of tension.

Figure 3 illustrates the principle of fitting together of measurement points.

Figure 4 illustrates a profile of modulus of elasticity of a paper web.

15

Figure 5 illustrates a profile of irreversible stretch of a paper web.

Fig. 1 shows a typical location of an apparatus 10 for measurement of the tension profile in a paper machine. In this exemplifying embodiment, the measurement  
20 apparatus has been fitted in the dry end of the paper machine between a calender 20 and a reel-up 30. The measurement data 11 concerning the tension profile are passed along a bus to a data processing equipment 14. The tension profile is measured at different tension levels so that the stretch of the paper web W between the calender 20 and the reel-up 30 is adjusted. A change in the stretch is produced so that the  
25 web W speeds in the calender nip and in the reeling nip are altered. In this way, a difference in speed is produced between the calender and the reel-up. The relative stretch  $\varepsilon$  that was present when each tension profile was measured is determined from the formula:

30

$$\varepsilon = \frac{v_2 - v_1}{v_1}$$

wherein

$v_1$  = web speed in the calender nip

$v_2$  = web speed in the reeling nip.

5 The data processing equipment 14 gives commands concerning the regulation of the different speeds to the regulation units 12 and 13 for the drives whose speeds can be regulated. The regulation unit 12 controls the calender nip, and the regulation unit 13 controls the reeling nip. After the desired tension profiles have been measured at a number of, preferably three, different tension levels, the data processing equipment  
10 14 computes the profiles 15 of irreversible stretch and of dynamic modulus of elasticity by means of the fitting method that will be described later. These profiles can be displayed in a display apparatus 17, which can be, e.g., a display monitor or a printer. The profiles 15 are used for making the regulations of the papermaking process by means of the control unit 16 of the paper machine. The control unit 16  
15 can be based on automatic feedback regulation and/or on manual regulation.

Fig. 2 shows a measurement result obtained by means of the apparatus 10 for measurement of the tension profile, wherein the tension profile has been measured at three different known tension levels  $T_1(y)$ ,  $T_2(y)$  and  $T_3(y)$ , which levels correspond to the values of relative stretch  $\varepsilon_1$ ,  $\varepsilon_2$  and  $\varepsilon_3$ . In the figure, the vertical axis  
20 represents the tension as the units N/m (newtons per metre). The horizontal axis represents the location  $y$  in the cross direction of the paper web, the unit being mm (millimetre). In this example, the width of the paper web is 7 metres. In Fig. 2, as an example, the tension values  $T_1(1000)$ ,  $T_2(1000)$  and  $T_3(1000)$  corresponding to  
25 a cross-direction distance of 1000 mm of the paper web have been indicated in respect of each graph of tension profile  $T_1(y)$ ,  $T_2(y)$  and  $T_3(y)$ .

Fig. 3 illustrates the principle with which the tension values measured with each stretch value  $\varepsilon_1$ ,  $\varepsilon_2$  and  $\varepsilon_3$  are fitted in the curve. This fitting is carried out at each  
30 point of measurement of the tension profile. The fitting of a straight line at the measurement points is carried out, for example, by making use of the method of

fitting of the least squares. The equation of the straight line drawn in Fig. 3 has the following form:

$$T(y) = m(y)E(y)(\varepsilon - \varepsilon_0)^n$$

5

wherein

$T(y) = T_1(y), T_2(y), T_3(y) =$  tension profile [N/m]

$m(y) =$  basis weight profile [kg/sq.m]

$E(y) =$  dynamic modulus of elasticity [sq.m/s<sup>2</sup>]

10  $\varepsilon = \varepsilon_1, \varepsilon_2 \text{ and } \varepsilon_3 =$  relative stretch

$\varepsilon_0 =$  irreversible stretch

$n \approx 1$

By means of the straight line fitted on the measurement results, illustrated in Fig. 3, it is possible to determine the irreversible stretch  $\varepsilon_0$  from the measurement results, which irreversible stretch is obtained from the intersection point of the straight line on the horizontal axis. The angle coefficient of the straight line corresponds to the dynamic modulus of elasticity  $E(y)$  of the measurement point.

20 Fig. 4 shows the CD profile of the dynamic modulus of elasticity  $E$  of the paper web determined in the way described above. In the figure, the vertical axis represents the elasticity module  $E$ , whose unit is sq.m/s<sup>2</sup>, and the horizontal axis represents the location on the paper web  $W$  in the CD direction.

25 Fig. 5 shows the profile of the irreversible stretch  $\varepsilon_0$  of the paper web  $W$  determined in the way described above. In the figure, the vertical axis represents the irreversible stretch  $\varepsilon_0$  as a percentage, and the horizontal axis represents the location in the cross-direction of the paper web  $W$ .

30 Above, an exemplifying embodiment has been described, according to which the measurement of the tension profile is carried out between a calender and a reel-up, i.e. in the dry end of the paper machine. The method can also be applied to other



parts of a paper machine. Possible other locations of measurement are, for example, the press section, a coating machine, and an off-line calender. In such a case, the determination of the quantities differs to some extent from what has been stated above, because the stretch/tension conduct of the paper depends on the degree of dryness of the paper.

In the following, the patent claims will be given, and the different details of the invention may show variation within the scope of the inventive idea defined in said claims and differ from what has been stated above by way of example only.

10

## Claims

1. A method for determination of an irreversible stretch and of a dynamic modulus of elasticity from a paper web (W), **characterized** in that the method comprises the following steps:
- 5
- the paper web (W) is subjected to an on-line measurement of its cross-direction tension profile at two or more different tension levels,
  - a curve is fitted to the number of points of tension measurement carried out at each location of measurement in the cross direction of the paper web (W),
  - 10 — the irreversible stretch ( $\epsilon_0$ ) is determined from each fitted curve, and
  - the dynamic modulus of elasticity (E) is determined from each fitted curve.
2. A method as claimed in claim 1, **characterized** in that the determined values and/or profiles of irreversible stretch ( $\epsilon_0$ ) and of dynamic modulus of elasticity (E) are used for the control of the papermaking process.
- 15
3. A method as claimed in claim 2, **characterized** in that the levels of tension of the paper web (W) are varied by means of a web (W) speed difference ( $v_2 - v_1$ ).
- 20
4. A method as claimed in any of the claims 1 to 3, **characterized** in that the results of measurement of irreversible stretch ( $\epsilon_0$ ) and of dynamic modulus of elasticity (E) provided by means of the method in accordance with the invention are utilized for the control of the papermaking process manually.
- 25
5. A method as claimed in any of the claims 1 to 4, **characterized** in that the control of the papermaking process is carried out as on-line feedback control by means of an automation system so that set values or certain target areas of target values are assigned to said levels and/or profiles of irreversible stretch ( $\epsilon_0$ ) and
- 30 dynamic modulus of elasticity.

6. A method as claimed in any of the claims 1 to 5, **characterized** in that the measurement of the tension profile is carried out in the dry end of the paper machine.
- 5 7. A method as claimed in any of the claims 1 to 5, **characterized** in that the measurement of the tension profile is carried out on the run of the web (W) between an on-line calender (20) and a reel-up (30).
8. A method as claimed in any of the claims 1 to 5, **characterized** in that the  
10 measurement of the tension profile is carried out in the press section.
9. A method as claimed in any of the claims 1 to 5, **characterized** in that the measurement of the tension profile is carried out in a coating machine.
- 15 10. A method as claimed in any of the claims 1 to 5, **characterized** in that the measurement of the tension profile is carried out in an off-line calender.
11. A method for the control of a papermaking process, **characterized** in that, in the method, a method as claimed in the claims 1 to 10 is used for regulation of the  
20 dynamic modulus of elasticity (E) and/or of the irreversible stretch ( $\epsilon_0$ ).
12. A method as claimed in claim 11, **characterized** in that the profiles of irreversible stretch ( $\epsilon_0$ ) and/or of dynamic modulus of elasticity (E) are affected by means of the following parameters and/or devices of the papermaking process: devices for  
25 regulation of basis weight, moisture content and thickness, such as slice spindles and dilution valves of the headbox, steam box in the press section and wire loads in nips, moistening device, wire loads and/or steam boxes in a calender.




FIG. 1

2/4




FIG. 2




FIG. 3





FIG. 4

**FIG. 5**

## INTERNATIONAL SEARCH REPORT

International application No.

PCT/FI 99/00138

## A. CLASSIFICATION OF SUBJECT MATTER

IPC6: G01N 33/34, G01N 3/08, B65H 77/00

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC6: G01N

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

SE,DK,FI,NO classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

WPI,PAJ

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0311507 A2 (MEASUREX CORPORATION), 12 April 1989 (12.04.89), column 5, line 28 - column 6, line 8; column 8, line 8 - line 27; column 14, line 20 - column 15, line 63, column 16, line 45 - line 62; figures 1,2, 5,8; claims 6,20,21,24; abstract  --	1-12
X	US 3718037 A (PETER JACK ELTON CRAWFORD STRINGER ET AL), 27 February 1973 (27.02.73), column 1, line 4 - line 11; column 1, line 39 - line 50; column 2, line 39 - line 46, column 3, line 7 - line 10; column 4, line 21 - line 66; figures 1,4; claim 13; abstract  --	1-12



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents:	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
"A" document defining the general state of the art which is not considered to be of particular relevance	"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
"E" earlier document but published on or after the international filing date	"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"&" document member of the same patent family
"O" document referring to an oral disclosure, use, exhibition or other means	
"P" document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search

18 June 1999

Date of mailing of the international search report

28-06-1999

Name and mailing address of the ISA/  
Swedish Patent Office  
Box 5055, S-102 42 STOCKHOLM  
Facsimile No. +46 8 666 02 86

Authorized officer

Bertil Dahl/MP  
Telephone No. +46 8 782 25 00



## INTERNATIONAL SEARCH REPORT

International application No.

PCT/FI 99/00138

## C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 4866984 A (PAUL J. HOUGHTON), 19 Sept 1989 (19.09.89), column 3, line 60 - column 4, line 7; column 4, line 42 - line 65, claims 2,4,31, abstract  --	1-5,11,12
A	EP 0826821 A2 (VOITH SULZER PAPIERMASCHINEN GESELLSCHAFT MBH), 4 March 1998 (04.03.98)  -- -----	1-12

Form PCT/ISA/210 (continuation of second sheet) (July 1992)

INTERNATIONAL SEARCH REPORT  
Information on patent family members

01/06/99

International application No.

PCT/FI 99/00138

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0311507 A2	12/04/89	SE 0311507 T3	
		CA 1329245 A	03/05/94
		DE 3854843 D,T	08/08/96
		DE 3872479 A	06/08/92
		EP 0464958 A,B	08/01/92
		SE 0464958 T3	
		FI 95840 B,C	15/12/95
		FI 884563 A	06/04/89
		JP 1162890 A	27/06/89
		US 5013403 A	07/05/91
		US 5104488 A	14/04/92
US 3718037 A	27/02/73	CA 919937 A	30/01/73
		DE 2057798 A	09/06/71
		FR 2072248 A	24/09/71
		GB 1328661 A	30/08/73
		JP 51044428 B	29/11/76
		SE 361526 B	05/11/73
US 4866984 A	19/09/89	US 4864851 A	12/09/89
		US 4991432 A	12/02/91
		CA 1324445 A	16/11/93
		DE 3751473 D,T	22/02/96
		DE 3787227 D,T	07/04/94
		EP 0253644 A,B	20/01/88
		SE 0253644 T3	
		EP 0541518 A,B	12/05/93
		FI 92108 B,C	15/06/94
		FI 94803 B,C	14/07/95
		FI 873167 A	19/01/88
		FI 941622 A	08/04/94
		JP 2735547 B	02/04/98
		JP 63106556 A	11/05/88
EP 0826821 A2	04/03/98	CN 1190684 A	19/08/98
		DE 19634997 A	05/03/98
		JP 10183485 A	14/07/98